

# Techno Anti Stripping Agent

Sr. No.	Test	Method	Limit
1.	Appearance	Visual	Liquid / Solid
2.	Odour	Smelling	Agreeable
3.	Specific Gravity 27°C	IS:1202/78	0.860-1.03
4.	Water content % vol. Max.	IS:1448	1.0
5.	Solubility in diesel Oil (HDO or LDO) in ratio 2:98 at 50°C	Given in MORT&H Appendix	Completely Soluble
6.	Stripping value with bitumen containing 1% wt. Antistripping Agent at 40°C 24 hrs.	IS:6241 Appendix - 5	NO STRIPPING observed
7.	Under water coating test with 1% wt.antistripping agent	Given In MORT&H Appendix-5	Complete Coating observed
8.	Thermal Stability at 163°C hrs. 1% antistripping agent used	Given In MORT&H Appendix-5	Satisfactory e

